

Tecnoflon® PFR 94 perfluoroelastomer

Tecnoflon® PFR 94 is a chemical resistant perfluoroelastomer (FFKM). Tecnoflon® PFR 94 offers the widest range of aggressive media sealing capabilities along with excellent compression set values.

Tecnoflon® PFR 94 is suitable for most applications in temperature ranging from -10 °C to 230 °C, offering outstanding resistance to aggressive media such as hot organic and inorganic acids, caustics, ketones, aldehydes, esters, ethers, alcohols, fuels, solvents, sour gases, hydrocarbons, steam, hot water, ethylene and propylene oxide and mixed process streams. Moreover it can cope with a wide range of potent active pharmaceutical ingredients (APIs) and aggressive cleaning agents, being especially suited to withstand steam-in-place (SIP) and clean-in-place (CIP) procedures. PFR 94 can be combined with the cure system and other typical fluoroelastomer compounding ingredients; its mixing can be accomplished with two-roll mills or internal mixers. Finished goods may be produced by a variety of rubber processing methods.

The primary use for PFR 94 is the manufacturing of any kind of elastomeric sealing element such as O-rings, gaskets, valve bodies, butterfly valves, pump housings and stators,

metal bonded parts, diaphragms, profiles, etc. These sealing elements can be used in mechanical seals, pumps, compressors, valves, reactors, mixers, sprayers, dispensers, quick connect couplings, controls, instrumentation, etc. in a wide range of industrial sectors, such as semiconductor manufacturing, chemical process industry, oil & gas, food and pharma and paint spray.

Tecnoflon® PFR 94 is registered in the FDA Inventory of Effective Premarket Notifications for Food Contact Substances. It can be compounded so that the finished gaskets or seals can be used in food processing equipments (see "food processing compounds" section on pages 7-8-9).

Tecnoflon® PFR 94 is marketed in the form of raw polymer (1 kg box) in order to give the transformer the freedom and the opportunity to develop and fine-tune compounds and items best suited to the final application.

General

Material Status	• Commercial: Active		
Availability	• Europe	• North America	
Features	• Acid Resistant • Alcohol Resistant • Food Contact Acceptable	• Fuel Resistant • Good Chemical Resistance • Low Compression Set	• Moisture Resistant • Solvent Resistant • Steam Resistant
Uses	• Blending • Compounding • Diaphragms	• Gaskets • Profiles • Pump Parts	• Seals • Valves/Valve Parts
Agency Ratings	• FDA Food Contact, Unspecified Rating		
Appearance	• Translucent		
Forms	• Slab		
Processing Method	• Compounding		

Physical

	Typical Value	Unit	Test method
Mooney Viscosity ¹ (ML 1+10, 121°C)	35	MU	No Standard

Tecnoflon® PFR 94

perfluoroelastomer

Notes

Typical properties: these are not to be construed as specifications.

¹ Raw polymer



www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Material Safety Data Sheets (MSDS) are available by emailing us or contacting your sales representative. Always consult the appropriate MSDS before using any of our products. Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2013 Solvay Specialty Polymers. All rights reserved.